## 電解放出型走査電子顕微鏡観察下での薬用ハイドロキシアパタイト配合歯磨材 を用いたプラッシング後の脱灰エナメル質表面形態について

西村一行、山口芳功、吉武一貞

日本口腔科学会雑誌、第48巻、第3号、199-210、1999

## <Abstract >

The deposition from of hydroxyapatite on the enamel surface cannot be observed under high magnification with conventional SEM because of charging of the tooth. However, using FE-SEM, which made it possible to maintain a low acceleration voltage, minute structures of the enamel surface have been observed under high magnification. These observations were made without damaging the specimen or charging the tooth. This study was carried out to investigate the influence of medical hydroxyapatyte, which acted on the decalcified enamel surface of teeth microstructurally. The enamel surface of sound, caries-free human molars was decalcified with 0.1M HCL solution for five minutes in vitro. The enamel surface was treated by toothpaste containing medical hydroxyapatite, a control toothpaste, and a popular toothpaste. The surface from and crystal from was observed using FE-SEM, and the results were compared. The enamel surface treated with toothpaste containing medical hydroxyapatite was smooth under low magnification, and the gap of the enamel prism was covered by minute crystal particles(30-60nm) in a high magnification FE-SEM image. The enamel surface treated with the control toothpaste and the popular brand of toothpaste was not smooth under low maginihications, and an enamel prism from was confirmed in a high magnification FE-SEM image. These results suggested that the possibility of the crystal particle being medical hydroxyapatite was high, and toothpaste containing medical hydroxyapatite contributed to recrystalization of the decalcified enamel surface.

**Key words** : Medical hydroxyapatite(薬用ハイドロキシアパタイト),FE-SEM(電界放出型走査電子顕微鏡),Recryetalized(再結晶化エナメル質),

[Received Oct.19,1998, Accepted Jan.30,1999]